

**NATIONWIDE CHEMICAL COATING MFRS., INC.**

U.S. Toll Free: 1.800.423.7264 - 941.753.7500 - Fax: 941.753.1773

**TECHNICAL PRODUCT DATA SPREADSHEET**Revision Date:  
2/15/2007

Product Code #	Product Category and Description	Vehicle Resin Base	Pounds per Gal.	Solids by Weight	Solids by Volume	Pigment Volume	V.O.C. lbs/gal	V.O.C. gm/ltr	Dry to Touch	ReCoat Time	Cure Time	Spread Rate sq.ft./gal.
<b>INTERIOR CERAMIC PAINTS</b>												
1500	CERAMIC SHIELD™ FLAT Ceramic Paint	Modified Acrylic	11.6	51%	32%	56%	0.73	87.6	2-4 Hrs.	4 Hrs.	5-7 Days	250-400
1525	CERAMIC SHIELD™ SATIN Ceramic Paint	Acrylic	11.4	52%	36%	38%	0.75	90.0	2-4 Hrs.	4 Hrs.	5-7 Days	250-400
1550	CERAMIC SHIELD™ SEMI-GLOSS Paint	Acrylic	11.2	54%	37%	28%	0.91	109.2	2-4 Hrs.	4 Hrs.	5-7 Days	250-400
1590	CERAMIC SHIELD™ Ceramic Primer	Modified Acrylic	10.9	52%	35%	31%	0.43	51.6	2-4 Hrs.	4 Hrs.	5-7 Days	250-400
<b>EXTERIOR CERAMIC PAINTS</b>												
2500	CERAMIC FORCE® FLAT Ceramic Paint	Acrylic	11.8	52%	37%	52%	0.63	75.6	2-4 Hrs.	4 Hrs.	5-7 Days	200-350
2525	CERAMIC FORCE® SATIN Ceramic Paint	Acrylic	11.3	52%	36%	36%	0.75	90.0	2-4 Hrs.	4 Hrs.	5-7 Days	200-350
2550	CERAMIC FORCE® SEMI-GLOSS Paint	Acrylic	11.1	55%	38%	29%	1.27	152.4	2-4 Hrs.	4 Hrs.	5-7 Days	200-350
2590	CERAMIC FORCE® Ceramic Primer	Modified Acrylic	11.2	56%	42%	31%	0.38	45.6	2-4 Hrs.	4 Hrs.	5-7 Days	200-350
2595	CHALK FORCE™ High Ph & Chalk Sealer	Acrylic	8.9	9%	8%	0%	0.58	69.4	1-2 Hrs.	2 Hrs.	5-7 Days	300-400
<b>INT/EXT LATEX ENAMEL</b>												
5725	WEATHER-GUARD™ FLAT Latex Enamel	Acrylic	10.5	48%	38%	N/A	N/A	N/A	2-4 Hrs.	4 Hrs.	5-7 Days	200-300
5750	WEATHER-GUARD™ SEMI-GLOSS Enamel	Acrylic	10.3	45%	37%	N/A	N/A	N/A	2-4 Hrs.	4 Hrs.	5-7 Days	200-300
<b>ELASTOMERIC WALL COATINGS</b>												
2790	ULTRA PRIME™ Adhesive Primer Sealer	Elastomeric	8.8	41%	36%	0%	1.77	212.4	1-2 Hrs.	4 Hrs.	5-7 Days	100-175
2725	ULTRA SEAL™ Ceramic Wall Coating	Elastomeric	11.6	66%	47%	41%	0.68	81.6	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
2730	ULTRA SATIN™ Ceramic Wall Coating	Elastomeric	11.1	52%	40%	N/A	0.74	88.8	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
2825	ULTRA TEX™ Textured Wall Coating	Elastomeric	10.8	63%	43%	40%	0.61	73.2	2-4 Hrs.	12 Hrs.	5-7 Days	40-75
4025	ULTRA KOTE™ Industrial Coating	Elastomeric	11.7	68%	48%	39%	0.83	99.6	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
4030	ULTRA KOTE XL™ Max-Ceramic Coating	Elastomeric	10.5	59%	48%	N/A	N/A	N/A	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
2700	ULTRA CLEAR™ Clear Gloss Sealer	Acrylic	8.8	27%	24%	0%	N/A	N/A	1-2 Hrs.	2 Hrs.	5-7 Days	250-350
<b>ELASTOMERIC ROOF COATINGS</b>												
7090	ROOF-PRIME Vinyl Primer Sealer	Modified Acrylic	10.9	52%	37%	48%	N/A	N/A	2-4 Hrs.	6 Hrs.	5-7 Days	100-200
7000	KOOL-KOTE™ Reflective Roof Coating	Modified Acrylic	11.2	54%	38%	41%	1.29	154.8	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7020	SNOWBRITE™ Ceramic Roof Coating	Elastomeric	11.4	62%	44%	42%	0.60	72.0	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7030	INSULKOTE™ Ceramic Roof Coating	Elastomeric	11.5	63%	44%	42%	0.56	67.2	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7540	PERMAPATCH™ Elastomeric Caulk	Elastomeric	11.7	64%	40%	N/A	N/A	N/A	2-4 Hrs.	12 Hrs.	5-7 Days	144 Cu. In.
7590	PERMAFIBE™ Liquid Seam Sealer	Elastomeric	9.4	42%	37%	N/A	N/A	N/A	2-4 Hrs.	6 Hrs.	5-7 Days	50-75
7595	PERMABOND™ Adhesive Primer Sealer	Elastomeric	8.8	40%	36%	0%	1.77	212.4	1-2 Hrs.	4 Hrs.	5-7 Days	75-150
5790	METAL PRIME Red Iron Oxide Primer	Acrylic	11.9	79%	43%	N/A	1.63	195.6	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7525	PERMAKOTE® Ceramic Roof Coating	Elastomeric	11.6	63%	44%	40%	0.58	69.4	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7550	PERMAKOTE® SEMI-GLOSS Roof Coating	Elastomeric	11.1	51%	42%	N/A	0.74	88.8	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7575	PERMAKOTE® SILVER SEAL Coating	Elastomeric	10.2	52%	37%	N/A	0.80	95.6	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7530	PERMAKOTE PLUS® LPWF Roof Coating	Elastomeric	11.4	64%	50%	39%	0.50	60.2	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
7500	PERMACLEAR™ Clear Roof Finish	Acrylic	8.8	27%	24%	0%	N/A	N/A	1-2 Hrs.	2 Hrs.	5-7 Days	250-350
<b>MISCELLANEOUS PRODUCTS</b>												
4000	ENCAPSULGUARD™ Encapsulment	Acrylic	11.7	67%	47%	N/A	N/A	N/A	2-4 Hrs.	12 Hrs.	5-7 Days	100-150
4750	AQUAKOTE™ Industrial Paint/Stain	Acrylic	10.2	44%	33%	N/A	1.24	148.8	2-4 Hrs.	6 Hrs.	5-7 Days	250-350
5400	PRO-SEAL LINK 50% Vinyl Acrylic Resin	Vinyl Acrylic	8.7	50%	48%	0%	N/A	N/A	2-4 Hrs.	12 Hrs.	5-7 Days	250-350
5500	WATER SEAL Acrylic Silicone Sealer	Acrylic	8.5	21%	20%	0%	0.59	70.8	1-2 Hrs.	2 Hrs.	5-7 Days	350-450
5495	CRETE CLEAR Acrylic Sealer	Acrylic	8.8	30%	28%	0%	1.17	140.4	2-4 Hrs.	4 Hrs.	5-7 Days	300-400
5460	CRETE GUARD Acrylic Paint/Stain	Acrylic	10.4	40%	30%	N/A	1.40	168.0	2-4 Hrs.	6 Hrs.	5-7 Days	250-350
5875	ACRATHANE™ Commercial Paint/Stain	Acrylic	10.6	42%	32%	N/A	1.32	158.4	2-4 Hrs.	6 Hrs.	5-7 Days	250-350
5695	WOOD-TECH™ Clear Gloss Finish	Acrylic	8.8	27%	27%	0%	N/A	N/A	1-2 Hrs.	4 Hrs.	5-7 Days	250-350

Data has a variance of +/- 2%. N/A designates this information was not available at the time it was prepared. Data is based on temperature of 70° Fahrenheit and 50% Relative Humidity. Full Cure on Most Products can be up to 30 Days  
All information presented herein has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief; but is not guaranteed to be so